

Boron Carbide (B4C) Evaporation Pieces

Material Type	Boron Carbide	Z Ratio	**1.00
Symbol	B4C	E-Beam	Excellent
Melting Point (°C)	2,350	E-Beam Crucible Liner Material	Fabmate®, Graphite
Theoretical Density (g/cc)	2.37		10-8: 2,500
Purity:	99.99%, 99.95%	Temp. (°C) for Given Vap. Press. (Torr)	10-6: 2,580
			10-4: 2,650