

Tungsten Oxide (WO₃) Evaporation Pieces

Material Type	Tungsten Oxide	Z Ratio	**1.00
Symbol	WO ₃	E-Beam	Good
Color/Appearance	Lemon Yellow, Solid	Thermal Evaporation Techniques	Boat: W
Melting Point (°C)	1,473	E-Beam Crucible Liner Material	Tungsten
Theoretical Density (g/cc)	7.16	Temp. (°C) for Given Vap. Press. (Torr)	10-4: 980
Purity:	99.95% 99.99%		