

Zirconium Oxide (ZrO₂) Evaporation Pieces

Material Type	Zirconium Oxide	Z Ratio	**1.00
Symbol	ZrO ₂	E-Beam	Good
Color/Appearance	White, Solid	Thermal Evaporation Techniques	Boat: W
Melting Point (°C)	~2,700	E-Beam Crucible Liner Material	Graphite, Tungsten
Theoretical Density (g/cc)	5.6	Temp. (°C) for Given Vap. Press. (Torr)	10-4: ~2,200
Purity:	99.999 % 99.99%	Export Control (ECCN)	1C234